


## Technical Data Sheet

### Identification

	<b>Example:</b> M110E300 1T
	<b>M:</b> Chopped Strand Mat
	<b>11:</b> E-glass
	<b>0:</b> High splitting chopping roving
	<b>E:</b> Emulsion binder
	<b>300:</b> Nominal weight per square meter(g/m <sup>2</sup> )
<b>1T:</b> One edge	

### Specifications

Item	Standard NO.	Standard	Remark
Area Weight(g/m <sup>2</sup> )	ISO 3374	300±10%	
Moisture Content(%)	ISO 3344	≤0.20	
Loss On Ignition(%)	ISO 1887	3.0~4.6	
Tensile Strength(N)	ISO3342	≥40	

### Packing

Each Roll Packing								
Roll Diameter		Roll Length		N.W.		Width		Packing Material
mm	inch	m	yds	kg	lbs	mm	inch	
280	11	96	105	37.44	82.54	1300	51	
Each Pallet Packing								
Width (mm)	Packing/pallet	Rolls/pallet	N.W.		G.W.		Pallet Sizes	
			kg	lbs	kg	lbs	mm	inch
1300	4rolls×4layers (vertical pallet)	16	599.04	1321	703.04	1550	1140x1140x1460	45x45x57
	4rolls×3layers (horizontal pallet)	12	449.28	990	493.28	1087	1330x1140x970	52x45x38
	4rolls×2layers (horizontal pallet)	8	299.52	660	335.52	740	1330x1140x700	52x45x28

Remark: All packing is standard packing. Neutral packing & Customized packing to be discussed.

Technical Data Sheet

Each Container Packing				
Container Type	Size	Load	N.W.	G.W.
20'FCL	5.87m×2.33m×2.35m 19.3ft×7.6ft×7.7ft	Bottom:10pallets(16roll/vertical pallet) Up:10pallets(8roll/ horizontal pallet)	8985.6kg 19810lbs	9865.6kg 21750lbs
40'FCL	12m×2.33m×2.35m 39.3ft×7.6ft×7.7ft	Bottom:20pallets(16roll/vertical pallet) Up:20pallets(8roll/ horizontal pallet)	17971.2kg 39619lbs	17931.2kg 43499lbs
40'HC	12m×2.33m×2.66m 39.3ft×7.6ft×8.7ft	Bottom:20pallets(16roll/vertical pallet) Up:20pallets(12roll/ horizontal pallet)	20966.4kg 46222lbs	22886.4kg 50455lbs

**Storage**

It is recommended that the fiber glass products be stored in a cool and dry environment. The recommended temperature range of storage is between 10 ~ 30°C while the relative humidity is between 50 ~ 75%. The fiber glass products should remain in good packaging until using.

**Disclaimer**

As a service to customers, NMG Composites Co.,LTD may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by NMG in combination with other materials or systems.

NMG makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by NMG.

Specifications of reinforcements may change without notice.

**Issuer: Maggie Xie    Checker: Justin Mu    Date: 2016.01.11    Version No.: 2016-FR01**

**NMG COMPOSITES CO.,LTD**

Wanli Village Chongfu Town  
Tongxiang,Zhejiang,China,314511  
Tel: +86 573 88849111  
Fax: +86 573 88849112  
E-mail: [info@nmgchina.cc](mailto:info@nmgchina.cc) Web: [www.nmgchina.cc](http://www.nmgchina.cc)

**NMG EUROPA APS.**

Tel:+45 62201312 Fax: +45 62201477  
E-mail: [info@nmgeurope.eu](mailto:info@nmgeurope.eu) Web: [www.nmgeurope.eu](http://www.nmgeurope.eu)

**NMG USA,INC.**

Tel:+1 626 9652227 Fax:+1 626 9652227  
E-mail: [info@nmgamerica.us](mailto:info@nmgamerica.us) Web: [www.nmgamerica.us](http://www.nmgamerica.us)



*Composites Solutions Provider*