

Identification

	Example: M111P150H-1350
	M: Chopped Strand Mat
	11: E-glass
	1: Standard chopping roving
	P: Powder binder
	150: Nominal weight per square meter(g/m ²)
	H: Chopped strand mat for car headliner
1350: Width(mm)	

Specifications

Item	Standard NO.	Standard	Remark
Area Weight(g/m ²)	ISO 3374	150±10%	
Moisture Content(%)	ISO 3344	≤0.20	
Loss On Ignition(%)	ISO 1887	5~8	
Tensile Strength(N)	ISO3342	≥100	

Packing

Each Roll Packing								
Roll Diameter		Roll Length		Weight		Width		Packing Material
mm	inch	m	yds	kg	lbs	mm	inch	
280	11	150	164	30.38	67	1350	53	Carton
Each Pallet Packing								
Width (mm)	Packing/pallet	Rolls/pallet	N.W.		G.W.		Pallet Sizes	
			kg	lbs	kg	lbs	mm	inch
1350	4rolls×4layers (vertical pallet)	16	486.08	1072	538.08	1186	1140x1140x1510	45x45x59
	4rolls×3layers (horizontal pallet)	12	364.56	804	408.56	901	1380x1140x970	54x45x38
	4rolls×2layers (horizontal pallet)	8	243.04	536	279.04	615	1380x1140x700	54x45x28

Remark: All packing is standard packing. Neutral packing & Customized packing to be discussed.

Each Container Packing				
Container Type	Size	Load	N.W.	G.W.
20'FCL	5.87m×2.33m×2.35m 19.3ft×7.6ft×7.7ft	Bottom:10pallets(16rolls/vertical pallet) Up:8pallets(8rolls/ horizontal pallet)	6805.12kg 15003lbs	7613.12kg 16784bs
40'FCL	12m×2.33m×2.35m 39.3ft×7.6ft×7.7ft	Bottom:20pallets(16rolls/vertical pallet) Up:16pallets(8rolls/ horizontal pallet)	13610.24kg 30005lbs	15226.24kg 33568lbs
40'HC	12m×2.33m×2.66m 39.3ft×7.6ft×8.7ft	Bottom:20pallets(16rolls/vertical pallet) Up:16pallets(12rolls/ horizontal pallet)	15554.56kg 34292lbs	17298.56kg 38136lbs

Storage

It is recommended that the fiber glass products be stored in a cool and dry environment. The recommended temperature range of storage is between 10 ~ 30°C while the relative humidity is between 50 ~ 75%. The fiber glass products should remain in good packaging until using.

Disclaimer

As a service to customers, NMG Composites Co.,LTD may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by NMG in combination with other materials or systems.

NMG makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by NMG.

Specifications of reinforcements may change without notice.

Issuer: Maggie Xie

Checker: Justin Mu

Date: 2016.01.11

Version No.: 2016-FR01

NMG COMPOSITES CO.,LTD

Wanli Village Chongfu Town
Tongxiang,Zhejiang,China,314511

Tel: +86 573 88849111

Fax: +86 573 88849112

E-mail: info@nmgchina.cc Web: www.nmgchina.cc**NMG EUROPA APS.**

Tel:+45 62201312 Fax: +45 62201477

E-mail: info@nmgeurope.eu Web: www.nmgeurope.eu**NMG USA,INC.**

Tel:+1 626 9652227 Fax:+1 626 9652227

E-mail: info@nmgamerica.us Web: www.nmgamerica.us**Composites Solutions Provider**