


**Identification**

	<b>Example:</b> EWP30P-1000
	<b>EWP:</b> E-GLASS Woven Fabrics(Plain)
	<b>30:</b> Nominal weight per square meter(g/m <sup>2</sup> )
	<b>p:</b> Paraffin
	<b>1000:</b> Width(mm)

**Specifications**

Item		Standard NO.	Standard	Remark
Area Weight(g/m <sup>2</sup> )		ISO 3374	21±5%	
Fabric Count (ends/cm)	Warp	/	20±1	
	Weft		12±1	
Input(Tex)	Warp	/	8	
	Weft		4	
Moisture Content(%)		ISO 3344	≤0.20	
Loss On Ignition(%)		ISO 1887	0.8~1.2	

**Packing**

Each Roll Packing								
Roll Diameter		Roll Length		Weight		Width		Packing Material
mm	inch	m	yds	kg	lbs	mm	inch	
300	12	About 2000	2187	About 42	93	1000	39	Kraft paper
Each Pallet Packing								
Packing/pallet	Rolls/pallet	N.W.		G.W.		Pallet Sizes		
		kg	lbs	kg	lbs	mm	inch	
3rolls×3layers (horizontal pallet)	9	378	833	400	882	1140x1140x1020	45x45x40	

Remark: All packing is standard packing. Neutral packing &amp; Customized packing to be discussed.

Each Container Packing				
Container Type	Size	Load	N.W.	G.W.
20'FCL	5.87m×2.33m×2.35m 19.3ft×7.6ft×7.7ft	20pallets	7560kg 16667lbs	8000kg 17637lbs
40'FCL	12m×2.33m×2.35m 39.3ft×7.6ft×7.7ft	40pallets	15120kg 33334lbs	16000kg 35274lbs
40'HC	12m×2.33m×2.66m 39.3ft×7.6ft×8.7ft	40pallets	15120kg 33334lbs	16000kg 35274lbs

### Storage

It is recommended that the fiber glass products be stored in a cool and dry environment. The recommended temperature range of storage is between 10 ~ 30°C while the relative humidity is between 50 ~ 75%. The fiber glass products should remain in good packaging until using.

### Disclaimer

As a service to customers, NMG Composites Co.,LTD may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by NMG in combination with other materials or systems.

NMG makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by NMG.

Specifications of reinforcements may change without notice.

Issuer: Maggie Xie      Checker: Justin Mu      Date: 2016.01.11      Version No.: 2016-FR01

#### NMG COMPOSITES CO.,LTD

Wanli Village Chongfu Town  
Tongxiang,Zhejiang,China,314511  
Tel: +86 573 88849111  
Fax: +86 573 88849112  
E-mail: [info@nmgchina.cc](mailto:info@nmgchina.cc) Web: [www.nmgchina.cc](http://www.nmgchina.cc)

#### NMG EUROPA APS.

Tel:+45 62201312 Fax: +45 62201477  
E-mail: [info@nmgeurope.eu](mailto:info@nmgeurope.eu) Web: [www.nmgeurope.eu](http://www.nmgeurope.eu)

#### NMG USA,INC.

Tel:+1 626 9652227 Fax:+1 626 9652227  
E-mail: [info@nmgamerica.us](mailto:info@nmgamerica.us) Web: [www.nmgamerica.us](http://www.nmgamerica.us)



Composites Solutions Provider