


**Identification**

	<b>Example:</b> EWP400S-1000
	<b>EWP:</b> E-GLASS Woven Fabrics(Plain)
	<b>400:</b> Nominal weight per square meter(g/m <sup>2</sup> )
	<b>S:</b> Silane
	<b>1000:</b> Width(mm)

**Specifications**

Item		Standard NO.	Standard	Remark
Area Weight(g/m <sup>2</sup> )		ISO 3374	400±5%	
Fabric Count (ends/cm)	Warp	/	8±1	
	Weft		7±1	
Input(Tex)	Warp	/	272	
	Weft		272	
Moisture Content(%)		ISO 3344	≤0.20	
Loss On Ignition(%)		ISO 1887	0.8~1.2	

**Packing**

Each Roll Packing								
Roll Diameter		Roll Length		Weight		Width		Packing Material
mm	inch	m	yds	kg	lbs	mm	inch	
250	10	100	109	40	88	1000	39	Carton
Each Pallet Packing								
Packing/pallet	Rolls/pallet	N.W.		G.W.		Pallet Sizes		
		kg	lbs	kg	lbs	mm	inch	
4rolls×4layers (horizontal pallet)	16	640	1411	692	1526	1140x1140x1170	45x45x46	

Remark: All packing is standard packing. Neutral packing & Customized packing to be discussed.

Each Container Packing				
Container Type	Size	Load	N.W.	G.W.
20'FCL	5.87m×2.33m×2.35m 19.3ft×7.6ft×7.7ft	20pallets	12800kg 28219lbs	13840kg 30512lbs
40'FCL	12m×2.33m×2.35m 39.3ft×7.6ft×7.7ft	40pallets	25600kg 56438lbs	27680kg 61023lbs
40'HC	12m×2.33m×2.66m 39.3ft×7.6ft×8.7ft	40pallets	25600kg 56438lbs	27680kg 61023lbs

**Storage**

It is recommended that the fiber glass products be stored in a cool and dry environment.

The recommended temperature range of storage is between 10 ~ 30°C while the relative humidity is between 50 ~ 75%. The fiber glass products should remain in good packaging until using.

**Disclaimer**

As a service to customers, NMG Composites Co.,LTD may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by NMG in combination with other materials or systems.

NMG makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by NMG.

Specifications of reinforcements may change without notice.

**Issuer: Maggie Xie****Checker: Justin Mu****Date: 2016.01.11****Version No.: 2016-FR01****NMG COMPOSITES CO.,LTD**

Wanli Village Chongfu Town  
Tongxiang,Zhejiang,China,314511

Tel: +86 573 88849111

Fax: +86 573 88849112

E-mail: [info@nmgchina.cc](mailto:info@nmgchina.cc) Web: [www.nmgchina.cc](http://www.nmgchina.cc)**NMG EUROPA APS.**

Tel:+45 62201312 Fax: +45 62201477

E-mail: [info@nmgeurope.eu](mailto:info@nmgeurope.eu) Web: [www.nmgeurope.eu](http://www.nmgeurope.eu)**NMG USA,INC.**

Tel:+1 626 9652227 Fax:+1 626 9652227

E-mail: [info@nmgamerica.us](mailto:info@nmgamerica.us) Web: [www.nmgamerica.us](http://www.nmgamerica.us)**Composites Solutions Provider**