

Identification

	Example: M111E250H-1350
	M: Chopped Strand Mat
	11: E-glass
	1: Standard chopping roving
	E: Emulsion binder
	250: Nominal weight per square meter(g/m ²)
	H: Chopped strand mat for car headliner
1350: Width(mm)	

Specifications

Item	Standard NO.	Standard	Remark
Area Weight(g/m ²)	ISO 3374	250±10%	
Moisture Content(%)	ISO 3344	≤0.20	
Loss On Ignition(%)	ISO 1887	3~5	
Tensile Strength(N)	ISO3342	≥100	

Packing

Each Roll Packing								
Roll Diameter		Roll Length		Weight		Width		Packing Material
mm	inch	m	yds	kg	lbs	mm	inch	
280	11	100	109	33.75	74	1350	53	Carton
Each Pallet Packing								
Width (mm)	Packing/pallet	Rolls/pallet	N.W.		G.W.		Pallet Sizes	
			kg	lbs	kg	lbs	mm	inch
1350	4rolls×4layers (vertical pallet)	16	540	1190	592	1305	1140x1140x1510	45x45x59
	4rolls×3layers (horizontal pallet)	12	405	893	449	990	1380x1140x970	54x45x38
	4rolls×2layers (horizontal pallet)	8	270	595	306	675	1380x1140x700	54x45x28

Remark: All packing is standard packing. Neutral packing & Customized packing to be discussed.

Each Container Packing				
Container Type	Size	Load	N.W.	G.W.
20'FCL	5.87m×2.33m×2.35m 19.3ft×7.6ft×7.7ft	Bottom:10pallets(16rolls/vertical pallet) Up:8pallets(8rolls/ horizontal pallet)	7560kg 16667lbs	8368kg 18448lbs
40'FCL	12m×2.33m×2.35m 39.3ft×7.6ft×7.7ft	Bottom:20pallets(16rolls/vertical pallet) Up:16pallets(8rolls/ horizontal pallet)	15120kg 33334lbs	16736kg 36896lbs
40'HC	12m×2.33m×2.66m 39.3ft×7.6ft×8.7ft	Bottom:20pallets(16rolls/vertical pallet) Up:16pallets(12rolls/ horizontal pallet)	17280kg 38095lbs	19024kg 41940lbs

Storage

It is recommended that the fiber glass products be stored in a cool and dry environment. The recommended temperature range of storage is between 10 ~ 30°C while the relative humidity is between 50 ~ 75%. The fiber glass products should remain in good packaging until using.

Disclaimer

As a service to customers, NMG Composites Co.,LTD may provide computer-generated predictions of the physical performance of a product using a reinforcement fabric produced by NMG in combination with other materials or systems.

NMG makes no warranty whatsoever as to the accuracy of any such predicted physical performance, and customer acknowledges that customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a fabric or material produced or manufactured by NMG.

Specifications of reinforcements may change without notice.

Issuer: Maggie Xie Checker: Justin Mu Date: 2016.01.11 Version No.: 2016-FR01

NMG COMPOSITES CO.,LTD

Wanli Village Chongfu Town
Tongxiang,Zhejiang,China,314511
Tel: +86 573 88849111
Fax: +86 573 88849112
E-mail: info@nmgchina.cc Web: www.nmgchina.cc

NMG EUROPA APS.

Tel:+45 62201312 Fax: +45 62201477
E-mail: info@nmgeurope.eu Web: www.nmgeurope.eu

NMG USA,INC.

Tel:+1 626 9652227 Fax:+1 626 9652227
E-mail: info@nmgamerica.us Web: www.nmgamerica.us

