

### **Product Data Sheet: SphereCel HX Type CM**



# SPHERE CEL®

LAMINATE BULKER

- The cost effective solution for closed mold processes, infusion, LRTM, RTM, compression molding
- Used as core material
- Pressure stable nonwoven and compatible with all regular types of resins, including polyester, vinyl ester, phenolic and epoxy
- Used as infusion or resin transfer medium/core combination

### **CHARACTERISTICS**

#### Perforated

Mechanical Properties 1.5 mm	Unit	Value	Test Method
Flexural Strength	PSI	5800	ASTMD 790
Flexural Modulus	PSI	230000	ASTM D790
Tensile Strength across layers	PSI	1000	ASTM C297
Compressive Strength	PSI	510	ISO
Shear Strength	PSI	1400	ASTM C273
Shear Modulus	PSI	4500	ASTM C273

### **INDUSTRIES**

- Marine: hulls, decks and structures of boats and yachts
- Transportation: parts and panels of cars, trailers, trucks and RV's
- Mass transit: interior and exterior of trains, light rail and buses
- Leisure: kayaks, surfboards, pools and bath tubs
- Industrial: architectural panels, fans, containers and tanks
- Wind Energy: nacelle covers and blades

### **PROCESSING**

Regular established practices for composites closed mold lamination.

All tests carried out by independent laboratory. This information is provided in good faith and is subject to modifications without prior notification. It does not constitute a commitment, neither a contractual document. Carbon-Core Corp will not assume any liability form use or misuse of data presented herein. Assessment of suitability is the responsibility of end user only.



### **Product Data Sheet: SphereCel HX Type CM**

Product Description:	Non-woven core material			
Base material:	Proprietary veil, volumized with thermoplastic microspheres			
Thickness: (+/- 10%)	1.5 mm	2 mm	3 mm	
Weight: (+/- 15%)	100 g/m²	110 g/m²	125 g/m²	
Width: (+ 40 / - 20 mm)	100-300 cm	100-300 cm	100-300 cm	
Roll length:	90 m	70 m	50 m	
Weight per roll: (approx.)	9 kg	7.7 kg	6.3 kg	
Packaging:	Plastic bag			
Storage:	Material should be stored in original packaging, away from humidity, in well-ventilated rooms, at a moderate temperature.			

All tests carried out by independent laboratory. This information is provided in good faith and is subject to modifications without prior notification. It does not constitute a commitment, neither a contractual document. Carbon-Core Corp will not assume any liability form use or misuse of data presented herein. Assessment of suitability is the responsibility of end user only.



### **Product Data Sheet: SphereCel HX Type OM**



# SPHERE CEL®

LAMINATE BULKER

- The cost effective solution for open mold processes
- Used as core material
- Pressure stable nonwoven and compatible with all regular types of resins, including polyester, vinyl ester, phenolic and epoxy

### **CHARACTERISTICS**

#### Perforated

Mechanical Properties 2mm	Unit	Value	Test Method
Flexural Strength	PSI	2320	ASTMD 790
Flexural Modulus	PSI	14500 0	ASTM D790
Tensile Strength across layers	PSI	870	ASTM C297
Compressive Strength	PSI	580	ISO
Shear Strength	PSI	870	ASTM C273
Shear Modulus	PSI	5800	ASTM C273

### **INDUSTRIES**

- Marine: hulls, decks and structures of boats and yachts
- Transportation: parts and panels of cars, trailers, trucks and RV's
- Mass transit: interior and exterior of trains, light rail and buses
- Leisure: kayaks, surfboards, pools and bath tubs
- Industrial: architectural panels, fans, containers and tanks
- Wind Energy: nacelle covers and blades

### **PROCESSING**

Regular established practices for composites open mold lamination.

All tests carried out by independent laboratory. This information is provided in good faith and is subject to modifications without prior notification. It does not constitute a commitment, neither a contractual document. Carbon-Core Corp will not assume any liability form use or misuse of data presented herein. Assessment of suitability is the responsibility of end user only.



## **Product Data Sheet: SphereCel HX Type OM**

Product Description:	Non-woven core material			
Base material:	Proprietary veil, volumized with thermoplastic microspheres			
Thickness: (+/- 10%)	1.5 mm	2 mm	3 mm	
Weight: (+/- 15%)	95 g/m²	105 g/m²	120 g/m²	
Width: (+ 40 / - 20 mm)	100-300 cm	100-300 cm	100-300 cm	
Roll length:	90 m	70 m	50 m	
Weight per roll: (approx.)	8.6 kg	7.4 kg	6.0 kg	
Packaging:	Plastic bag			
Storage:	Material should be stored in original packaging, away from humidity, in well-ventilated rooms, at a moderate temperature.			

All tests carried out by independent laboratory. This information is provided in good faith and is subject to modifications without prior notification. It does not constitute a commitment, neither a contractual document. Carbon-Core Corp will not assume any liability form use or misuse of data presented herein. Assessment of suitability is the responsibility of end user only.